

Inspiring Great Spaces™

ArmstrongFlooring®

HETEROGENEOUS VINYL SHEET

DECORART™

Rejuvenations™ TimberLine®

Inspiring Great Spaces™

ArmstrongFlooring

HETEROGENEOUS VINYL SHEET

DECORART™

Rejuvenations™ TimberLine®

DecorArt™ Rejuvenations™ TimberLine®

Heterogeneous Vinyl Sheet



37524

WR: WR: FPWS227000

Maple Lane sugarcane



37523

WR: WR: FPWS228000

Maple Lane agave



37527

WR: WR: FPWS035000

Maple Lane maple syrup

DecorArt™ Rejuvenations™ TimberLine®

Heterogeneous Vinyl Sheet



37525

WR: WR: FPWS190000

Maple Lane honeycomb



37526

WR: WR: FPWS226000

Maple Lane golden nectar




37537

WR: FPWS199000

Maple Lane molasses

DecorArt™ Rejuvenations™ TimberLine®

Heterogeneous Vinyl Sheet



37532 **Walnut Street snow capped**
WR: FPWS238000



37533 **Walnut Street cabin**
WR: FPWS203000

DecorArt™ Rejuvenations™ TimberLine®

Heterogeneous Vinyl Sheet



37502 **Rustic Beech** sunscreen
WR: FPWS232000



37507 **Hickory Run** biscotti
WR: FPWS207000

HETEROGENEOUS VINYL SHEET

DecorArt™ Rejuvenations™ TimberLine®

TECHNICAL DATA

Characteristics	Standard	Unit	Result		
Type of flooring	ISO 10582 / EN 649		Heterogeneous vinyl sheet		
Surface treatment			DIAMOND 10™		
Pattern			Wood		
Safety Criteria					
Flammability	EN 13501-1	class	Bfl-s1		
Slip resistance	DIN 51130	group	R10		
Dynamic coefficient of friction	EN 13893	class	DS		
Limit of harmful substances	GB 18586		PASS		
Performance Behaviour					
Roll dimension	ISO 24341 / EN 426	m	2.0m x 15/23m		
Overall thickness	ISO 24346 / EN 428	mm	2.0		2.6
Thickness of wear layer	ISO 24340 / EN 429	mm	0.55	0.7	0.7
Residual indentation	ISO 24343-1 / EN 433	mm	< 0.1		
Dimensional stability	ISO 23999 / EN 434	%	< 0.4		
Wear resistance	EN 649	group	T		
Color fastness	ISO 105-B02	rating	≥ 6		
Castor wheel test	ISO 4918 / EN 425		Suitable		
Chemical resistance	EN 423		No stain 0		
Classification					
Commercial heavy / Industrial general (0.55mm)	ISO 10874 / EN 685	class	33 / 42		
Commercial very heavy / Industrial heavy (0.7mm)	ISO 10582 / EN 685	class	34 / 43		



www.vispac.co.th
 888 Moo 13, Bangna-Trad Road, Soi 45
 Bangkaew, Bangplee, Samutprakarn
 10540 Thailand
 Tel : (66-2) 316 0888
 Fax: (66-2) 316 5381
 E-mail: marketing@vispac.co.th

